

Declaration of Performance
(according to regulation EU No 305/2011)

No. LPE Plate S960QL

Plate S960QL / 1.8933 according EN 10025-6

To be used in-welded, bolted and riveted structures

Tata Steel UK Limited
Long Products Europe
PO Box 1, Brigg Road
Scunthorpe, DN16 1BP
Tel: +44 (0)1724 404040
Website : www.tatasteeleurope.com

CE Marking Notified Body
Lloyds Register Verification Limited
71 Fenchurch Street, London, EC3M 4BS
Tel :+44 (0)207 423 2428
Email : ecdirectives@lr.org
Website : www.lr.org

System of assessment and verification of constancy of performance of the product
System 2+

Notified factory production control certification body No. 0038 performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment, and evaluation of factory production control and issued the certificate of conformity of the factory production control

Essential characteristic	Performance				Harmonised technical specification
Tolerances on dimensions and shape	Thickness		EN 10029		EN10025-1 2004
	Flatness		EN 10029		
Yield strength (transverse)	Nominal thickness (mm)		Values Min (Mpa)		
	>	<=			
	-	50	960		
Tensile strength (transverse)	Nominal thickness (mm)		Values (MPa)		
	>	<=	min	max	
	5	50	980	1150	
Elongation (transverse)	Nominal thickness (mm)		Values min (% , 5.65√s ₀)		
	>	<=			
	-	-	10		
Impact strength (longitudinal)			30J at - 40°C		
Weldability CEV	Nominal thickness (mm)		Values max (%)		
	>	<=			
	-	50	0,82		
Durability	Nominal thickness (mm)		Values max (%)		
	-	-	C: 0,20 Si: 0,80 Mn: 1,70 P: 0,020 S: 0,010 N: 0,015 B: 0,0050 Cr: 1,50 Cu: 0,50 Mo: 0,70 Nb: 0,06 Ni: 2,0 Ti: 0,05 V: 0,12 Zr: 0,15		



0038

Tata Steel
Long Products Europe
PO Box 1, Brigg Road
Scunthorpe, UK

13

LPE Plate S960QL

EN 10025-1 – 2004

Plate S960QL / 1.8933

To be used in-welded, bolted and riveted structures

Tolerances on dimensions : Plate EN10029

Elongation :
Tensile Strength :
Yield Strength : EN10025-6
Impact Strength :
Weldability :
Durability :

Dangerous Substances : No Performance Determined

